

DURA PRO®

PRODUCT CHART

WOOD GLUES



**COLLE À BOIS
PVA TYPE 1
WOOD GLUE**



**COLLE À BOIS
PVA TYPE 2
WOOD GLUE**



**COLLE À BOIS
PVA TYPE 3
WOOD GLUE**



**COLLE À BOIS
PRISE RAPIDE
RAPID SET
WOOD GLUE**

Product code	AW0028	AW2539	AW3696	AW3649
Description	DURAPRO AW0028 is a high-performance adhesive for woodworking applications that are intended to be frequently exposed to variable climate conditions, and where high humidity resistance is essential.	DURAPRO AW2539 is suitable for end products that are intended to be exposed to weather, and for interiors projects where high humidity resistance or water resistance is beneficial.	DURAPRO AW3696 offers an excellent initial grip and reduced slippage during assembly. Forms strong bonds on hardwood, softwood, plywood, natural wood composites, MDF, cardboard and other porous materials.	DURAPRO AW3649 is used for bonding a wide variety of wood species in applications such as composite board, edgebanding and surface bonding. Contains a UV tracer for easier viewing with ultraviolet blacklight for removal of excess adhesive.
Color	Beige	White	Creamy Yellow	White
Viscosity (5/20 rpm/25°C)	3,500 – 4,200 cps	4,000 – 5,000 cps	5,000 – 6,000 cps	3,500 – 4,500 cps
Solids (%)	46 - 48	48 - 50	40 - 42	54 - 60
Density	1.08	1.11	1.08	1.08
Use	Indoor / Outdoor	Indoor / Outdoor	Indoor	Indoor
Water resistance	Very Good	Good	Poor	Poor
Open time	5 - 10 minutes	10 - 15 minutes	10 - 20 minutes	5 - 7 minutes
Clamp time	20 - 30 minutes	25 - 60 minutes	30 - 60 minutes	15 - 20 minutes
Available sizes	473 ml, 4 L, 15 L, 220 kg, 1100 kg	473 ml, 4 L, 15 L, 220 kg, 1100 kg	473 ml, 4 L, 15 L, 220 kg, 1100 kg	473 ml, 4 L, 15 L, 220 kg, 1100 kg
Country of origin	Canada	Canada	Canada	Canada

Made by:



Division of:
MULTIBOND Inc.
550, Marshall ave., Dorval (Québec) H9P1C9
1 800 361-2340

durapro-ca.com